



AW30 Click

Acoustic SPC - Clickvinyl - Lame vinyle - Designboden

Technical Specification - Technische Spezifikationen - Spécifications techniques - Technische specificaties

Description - Beschreibung - Description - Omschrijving	Rigid core SPC	
Thickness - Gesamtdicke - Epaisseur - Dikte	EN ISO 24337	4.20 mm + 1 mm IXPE acoustic backing
Total Weight - Flächengewicht - Poids Totale - Totaal gewicht	EN ISO 23997	ca. 8670 g/m ²
Wearlayer - Nuttschicht - Couche d'usure - Slijtlaag	EN ISO 24340	0.30 mm
Locking System - Verschlussystem - Système de verrouillage - Vergrendelingsysteem	Unilin®	
Bevels - Gefasste Kanten - Chanfrein - Afgeschuinde kanten	Micro Bevel 4 Sides	
Surface - Oberfläche - Surface - Toplaag	Ultra Mat	
Classification - Eignungsklasse - Classe d'usage - Gebruiksklasse	EN ISO 10874	23 Domestic Heavy - 31 Commercial Moderate



Performance - Leistungen - Prestaties

Reaction to fire - Brandverhalten - Classement feu - Brandklasse	EN 13501-1	Bfl-S1
Slip resistance - Rutschfest - Glissance - Antislip	EN 13893	DS
Slip restraint (dynamic coefficient of friction) - Rutschhemmung - Résistance au glissement - Slipweerstand	DIN 51130	R9
Thermal resistance R value - Wärmedurchlasswiderstand R - Résistance thermique R - Wamtedoorlaatweerstand R	EN 12664	0,076 (m ² .K)/W
Underfloor heating - Bodenheizung - Chauffage par le sol - Vloerverwarming	EN ISO 12524	Yes, max. 27°C
Electrostatic performance - Antistatik - Accumulation de charges électrostatiques - Electrostatische propensiteit	EN 1815	< 2 kV
Residual indentation - Eindrückverhalten - Poinçonnement rémanent - Restindruk	EN ISO 24343-1	< 0.2 mm pass
Dimensional stability - Massänderung - Stabilité dimensionnelle - Dimensionele stabiliteit	EN ISO 23999	≤ 0.10%
Curling - Schüsselung - Incurvation - Krulling	EN ISO 23999	pass
Castor chair resistance - Stuhllastenfestigkeit - Résistance aux chaises à roulettes - Bestand tegen stoelwielen	EN 425	pass, Type W
Colour fastness - Farbechtheit - Solidité de la couleur - Kleurechtheid	EN ISO 105-B02	> 6
Impact sound insulation - Trittschallverbesserungsmaß - Efficacité acoustique - Kontaktgeluidisolatie	EN ISO 717-2	17dB (ΔLw)
Chemical / Stain resistance - Fleckenbeständigkeit - Résistance aux taches - Vlekbestendigheid	EN ISO 26987	pass
Indoor AIR quality - French VOC regulation	ISO 16000	A+ certified
Content of pentachlorophenol		PCP under detection limit
Formaldehyde emissions (28 days test)	EN ISO 717-1	Class E1
Phthalate free		Yes
CE marking	EN 14041:2011	

Packaging - Verpackung - Emballage - Verpakking

Size and packaging wood	EN ISO 24342	181x1220 mm	10 planks / carton = 2.20 m ² / carton (Uniclic)
Size and packaging wood	EN ISO 24342	230x1500 mm	6 planks / carton = 2.07 m ² / carton (Unipush)

The technical data is correct at the time of printing. - 03/2025

