



SHI PRODUCT PASSPORT

Find products. Certify buildings.

SHI Product Passport No.:

2765-10-1023

PU-Schäume - 1K Pistolenschäume (B1 Schaum)

Product group: Construction chemicals - Construction Foam - PU foam - Polyurethane (PU)



fischerwerke GmbH & Co. KG
Klaus-Fischer-Straße 1
72178 Waldachtal



Product qualities:





SENTINEL HOLDING
INSTITUT



Köttner

Helmut Köttner
Scientific Director
Freiburg, 12 February 2026



Product:

PU-Schäume - 1K Pistolenschäume (B1 Schaum)

SHI Product Passport no.:

2765-10-1023



Contents

 SHI Product Assessment 2024	1
 DGNB New Construction 2023	2
 DGNB New Construction 2018	3
 BNB-BN Neubau V2015	4
 EU taxonomy	5
 BREEAM DE Neubau 2018	6
Product labels	7
Legal notices	8
Technical data sheet/attachments	9

The SHI Database is the first and only database for construction products whose comprehensive processes and data accuracy are regularly verified by the independent auditing company SGS-TÜV Saar





Product:

PU-Schäume - 1K Pistolenschäume (B1 Schaum)

SHI Product Passport no.:

2765-10-1023



SHI Product Assessment 2024

Since 2008, Sentinel Holding Institut GmbH (SHI) has been establishing a unique standard for products that support healthy indoor air. Experts carry out independent product assessments based on clear and transparent criteria. In addition, the independent testing company SGS regularly audits the processes and data accuracy.

Criteria	Product category	Harmful substance limit	Assessment	Notice
SHI Product Assessment	Sealants and adhesives	TVOC $\leq 300 \mu\text{g}/\text{m}^3$ Formaldehyd $\leq 24 \mu\text{g}/\text{m}^3$	Indoor Air Quality Certified (Advisory Note)	Achtung, Produkt enthält Isocyanate!



Product:

PU-Schäume - 1K Pistolenschäume (B1 Schaum)

SHI Product Passport no.:

2765-10-1023



DGNB New Construction 2023

The DGNB System (German Sustainable Building Council) assesses the sustainability of various types of buildings. It can be applied to both large-scale private and commercial projects as well as smaller residential buildings. The 2023 version sets high standards for ecological, economic, socio-cultural, and functional aspects throughout the entire life cycle of a building.

Criteria	No. / Relevant building components / construction materials / surfaces	Considered substances / aspects	Quality level
ENV 1.2 Local environmental impact, 03.05.2024 (3rd edition)	38 Installation foams that do not have to meet the requirements ⁸	VVOCs, VOCs, SVOC emissions, halogenated propellants, chlorinated paraffins, plasticisers, flame retardants	Quality level 2
Verification: Herstellererklärung vom 17.12.2025			

Criteria	No. / Relevant building components / construction materials / surfaces	Considered substances / aspects	Quality level
ENV 1.2 Local environmental impact, 29.05.2025 (4th edition)	38 Installation foams	VVOCs, VOCs, SVOC emissions, halogenated propellants, chlorinated paraffins, plasticisers, flame retardants	Quality level 2
Verification: Herstellererklärung vom 17.12.2025			



Product:

PU-Schäume - 1K Pistolenschäume (B1 Schaum)

SHI Product Passport no.:

2765-10-1023



DGNB New Construction 2018

The DGNB System (German Sustainable Building Council) assesses the sustainability of various types of buildings. It can be applied to both large-scale private and commercial projects as well as smaller residential buildings.

Criteria	No. / Relevant building components / construction materials / surfaces	Considered substances / aspects	Quality level
ENV 1.2 Local environmental impact	38 Installation foams that do not have to meet the requirements of class B1	Halogenated and other propellants solvents, plasticisers and flame retardants	Quality level 2
Verification: Herstellererklärung vom 17.12.2025			



Product:

PU-Schäume - 1K Pistolenschäume (B1 Schaum)

SHI Product Passport no.:

2765-10-1023



BNB-BN Neubau V2015

The Bewertungssystem Nachhaltiges Bauen (Assessment System for Sustainable Building) is a tool for evaluating public office and administrative buildings, educational facilities, laboratory buildings, and outdoor areas in Germany. The BNB was developed by the former Federal Ministry for the Environment, Nature Conservation, Building and Nuclear Safety (BMUB) and is now overseen by the Federal Ministry for Housing, Urban Development and Building (BMWSB).

Criteria	Pos. / product type	Considered substance group	Quality level
1.1.6 Risiken für die lokale Umwelt	33 Spray and mounting foams	Halogenated refrigerants / individual hazardous substances (formaldehyde)	Quality level 3

Verification: Herstellererklärung vom 17.12.2025



Product:

PU-Schäume - 1K Pistolenschäume (B1 Schaum)

SHI Product Passport no.:

2765-10-1023



EU taxonomy

The EU Taxonomy classifies economic activities and products according to their environmental impact. At the product level, the EU regulation defines clear requirements for harmful substances, formaldehyde and volatile organic compounds (VOCs). The Sentinel Holding Institut GmbH labels qualified products that meet this standard.

Criteria	Product type	Considered substances	Assessment
DNSH - Pollution prevention and control		Substances according to Annex C	EU taxonomy compliant
Verification: EMICODE EC1+-Zertifikat vom 25.07.2022			



Product:

PU-Schäume - 1K Pistolenschäume (B1 Schaum)

SHI Product Passport no.:

2765-10-1023



BREEAM DE Neubau 2018

BREEAM (Building Research Establishment Environmental Assessment Methodology) is a UK-based building assessment system that evaluates the sustainability of new constructions, refurbishments, and conversions. Developed by the Building Research Establishment (BRE), the system aims to assess and improve the environmental, economic, and social performance of buildings.

Criteria	Product category	Considered substances	Quality level
Hea 02 Indoor Air Quality	Interior adhesives and sealants (including flooring adhesives)	Emissions: Formaldehyde, TVOC, TSVOC, carcinogens	Exemplary quality
Verification: EMICODE EC1+-Zertifikat vom 25.07.2022			



Product:

PU-Schäume - 1K Pistolenschäume (B1 Schaum)

SHI Product Passport no.:

2765-10-1023



Product labels

In the construction industry, high-quality materials are crucial for a building's indoor air quality and sustainability. Product labels and certificates offer guidance to meet these requirements. However, the evaluation criteria of these labels vary, and it is important to carefully assess them to ensure products align with the specific needs of a construction project.



The EMICODE® label, awarded by the German manufacturers' association "GEV – Gemeinschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe und Bauprodukte e. V.", is primarily relevant for flooring installation materials. The EMICODE® EC1^{PLUS} label, as the premium class, sets significantly stricter emission limits than the other label variants.



Products bearing the Sentinel Holding Institute QNG-ready seal are suitable for projects aiming to achieve the "Qualitätssiegel Nachhaltiges Gebäude" (Quality Seal for Sustainable Buildings). QNG-ready products meet the requirements of QNG Appendix Document 3.1.3, "Avoidance of Harmful Substances in Building Materials." The KfW loan program Climate-Friendly New Construction with QNG may allow for additional funding.



This product is SHI Indoor Air Quality certified and recommended by Sentinel Holding Institut. Indoor-air-focused construction, renovation, and operation of buildings is made possible by transparent and verifiable criteria thanks to the Sentinel Holding concept.



Product:

PU-Schäume - 1K Pistolenschäume (B1 Schaum)

SHI Product Passport no.:

2765-10-1023



Legal notices

(*) These criteria apply to the construction project as a whole. While individual products can positively contribute to the overall building score through proper planning, the evaluation is always conducted at the building level. The information was provided entirely by the manufacturer.

Find our criteria here: <https://www.sentinel-holding.eu/de/Themenwelten/Pr%C3%BCfverfahren/C3%BCf-kriterien%20f%C3%BCr%20Produkte>

The SHI Database is the first and only database for construction products whose comprehensive processes and data accuracy are regularly verified by the independent auditing company SGS-TÜV Saar



Publisher

Sentinel Holding Institut GmbH
Bötzingen Str. 38
79111 Freiburg im Breisgau
Germany
Tel.: +49 761 590 481-70
info@sentinel-holding.eu
www.sentinel-holding.eu

PUP HF 750 B1 #45300

Merkmal	Wert	Einheit	Prüfvorschrift / Bemerk.
Chemische Basis	1K Polyurethan		
Farbe	grau		
Inhalt	750	ml	
Klebfreizeit	ca. 10	min	EN 17333-3
Schneidzeit	ca. 40	min	EN 17333-3
Baustoffklasse	B1		DIN 4102 – Teil 1*
Schaumausbeute, freigeschäumt	bis zu 45	l	EN 17333-1
Rohdichte	15 - 20	kg/m ³	
Standfestigkeit im Spalt	standfest		
Lagerhaltbarkeit	18	Monate	bei + 18 bis + 20 °C
Verarbeitungs-/Dosentemperatur	+ 10 bis + 25	°C	
Optimale Verarbeitungs-/Dosentemperatur	+ 20	°C	
Temperaturbeständigkeit	- 40 bis + 90	°C	ausgehärteter Schaum
Wärmeleitfähigkeit	ca. 0,035	W/m k	DIN 52612
Fugenschalldämmwert	56	dB	
Druckfestigkeit bei 10 % Stauchung	ca. 3	N/cm ²	DIN 53421
Treibmittelbasis	HFCKW-frei		
Aushärtung	chemisch durch Reaktion mit Luftfeuchtigkeit		

* Nur schwer entflammbar zwischen massiven, mineralischen oder metallischen Baustoffen. Fugentiefe und –breite bis 40 mm.

Anwendungshinweise

Dieser PU-Schaum haftet auf allen üblichen Baumaterialien, ausgenommen Polyethylen, Silikon, Teflon, Öle und Fette, o. ä.. Der ausgehärtete Schaum ist halbhart, elastisch, verrottungsfest, feuchtigkeitsbeständig und alterungsbeständig (vor UV-Strahlung schützen). Die Untergründe müssen fest, sauber, staub- und fettfrei sein.

Vor der Verarbeitung die Untergründe ausreichend mit Wasser befeuchten. Schichtdicken von mehr als 50 mm in mehreren Lagen schäumen und zwischenfeuchten. Zu kalte Dosen vorsichtig im lauwarmen Wasserbad erwärmen. Niemals über 50 °C erhitzen, da sonst Berstgefahr. Zu heiße Dosen im Wasserbad abkühlen.

Gelegentliches Schütteln unterstützt den Temperatenausgleich. Soweit nicht anders angegeben gelten die Angaben bei Standardbedingungen von 23 °C und 50 % r. F. und nicht gealtertem Schaum. Für die Prüfungen Ausbeute und Reaktivität sind mind. 85% r. F. erforderlich (gut vorfeuchten). Bei gealtertem Schaum sinkt die Ausbeute um bis zu 30%. Hierbei verkürzt sich auch die Klebfrei- und Schneidzeit. **Dose vor Gebrauch gut schütteln!**

Weitere Informationen zum Umgang entnehmen Sie bitte dem Sicherheitsdatenblatt; dieses enthält wichtige Hinweise.

Die Anwendungshinweise in diesem technischen Datenblatt sowie unsere anwendungstechnische Beratung in Wort und Schrift erfolgen nach bestem Wissen, beinhalten aber weder Zusagen an die Beschaffenheit oder Verwendbarkeit der Produkte noch selbständige oder unselbständige Garantiezusagen jeglicher Art.

Wir empfehlen vor Verwendung unserer Produkte stets die Eignung für den vorgesehenen Verwendungszweck konkret zu prüfen.

Aufgrund der Vielfalt der Anwendungsmöglichkeiten des einzelnen Produkts und den nicht einschätzbaren Gegebenheiten am Ort der Verarbeitung empfehlen wir darüber hinaus vor Verwendung die Funktion auf den Substraten vor Verwendung zu erproben.

Denzlingen, 17. Dezember 2025

Bestätigung fischer Polyurethanschäume

Sehr geehrte Damen und Herren,

hiermit bestätigen wir, dass die unten genannten Polyurethanschäume dem Anforderungskatalog des Qualitätssiegel Nachhaltiges Gebäude (QNG) entsprechen. Diese Produkte sind frei von halogenierten Treibmitteln und Formaldehyd, ebenfalls liegt der Gehalt an TCEP und Chlorparaffinen < 0,1 %. Alle genannten Produkte besitzen Emicode EC1 Plus.

Freundliche Grüße

fischerwerke GmbH & Co. KG

EIN UNTERNEHMEN DER UNTERNEHMENSGRUPPE FISCHER

Abt. Chemisches Labor

i. V. M. Vogel

Dr. Martin Vogel

i. A. Y. Herbstritt

Yvonne Herbstritt

Firmendaten

Telefon +49 7666 902-0
Telefax +49 7666 902-2929
Website www.fischer.de
GLN 40 06209 00000 7
USt-IDNr. DE 144252337
Anschrift:
Otto-Hahn-Str. 15, 79211 Denzlingen

Sitz

Klaus-Fischer-Straße 1, 72178 Waldachtal,
Deutschland
Registergericht Stuttgart HRA440255
Komplementär:
fischerinternational Beteiligungs GmbH,
Wiener Straße 95, 2514 Traiskirchen,
Österreich
Landesgericht Wiener Neustadt FN 319271 t

Geschäftsführer

Professor E. h. Senator E. h. E. h.
Dipl.-Ing. (FH) Klaus Fischer
Andreas Voll (Vorsitzender)
Maximilian Bronner, Dr. Oliver Geibig,
Jürgen Grün, Christian Hasenest
Marc-Sven Mengis, Claudia Rothe,
Matthias Schneider, Holger Thrun

Bankverbindung

Baden-Württembergische Bank
BLZ 600 501 01, Kto. 4 903 000
IBAN DE98 6005 0101 0004 9030 00
SWIFT SOLADEST600



Art. Nr.	Neue Bezeichnung	Bild
563227	Monomerarmer PU-Schaum PU-P EVO 750 B2	
543453	Flexibler Pistolenschaum PUP Flex 750 B2	
53084	Premium Pistolenschaum PUP Pro 825 B2	
503259	Premium Pistolenschaum PUP Pro 500 B2	
539197	Pistolenschaum Profi PUP S 750 B2	
40302	Pistolenschaum PUP S 750 B2	
539163	Pistolenschaum Profi PUP S 500 B2	
45300	Pistolenschaum schwer entflammbar PUP HF 750 B1	
513763	Brunnenschaum PUP BS 750 B2	
53080	Premium Schnellmontage- & Brunnenschaum PU Pro 750 B2	
50426	Premium Schnellmontage- & Brunnenschaum PU Pro 500 B2	
40301	Schnellmontageschaum Profi PU S 750 B2	
40300	Schnellmontageschaum PU S 500 B2	
506671	Perimeterklebeschaum PUP P 750 B2	
539164	WDVS Klebeschaum PUP WDVS 750	
53081	Schnellschaum Türzarge & Wanne PU 2K 400 B2	

Lizenzerteilung zur Führung des EMICODE

Lizenzierungs-Nummer: 15381/25.04.13

Für den Artikel Profi Baustoffe B1-Pistolenschaum PUFS 750

wird auf Antrag vom 22.07.2022

unter Bezugnahme auf die Einstufung gemäß den nach § 10 der
GEV-Zeichensatzung festgelegten Richtlinien

namens der Gemeinschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe
und Bauprodukte e.V. für den oben genannten Artikel nach § 5 Abs. 4 der
GEV-Zeichensatzung die Lizenz zur Führung des GEV-Zeichens



erteilt. Damit erfüllt dieser Artikel die rückseitig aufgeführten Kriterien.
Die Firma ist ordentliches Mitglied der GEV.

OM094 25.07.2022
gültig bis 25.07.2027

A handwritten signature in blue ink, appearing to read "D. Müller".

Der Geschäftsführer
Gemeinschaft Emissionskontrollierte Verlegewerkstoffe,
Klebstoffe und Bauprodukte e.V.
Völklinger Straße 4 · D-40219 Düsseldorf

Hinweise zu den Voraussetzungen über die Vergabe der Lizenz für den EMICODE

Das gemäß vorseitiger Lizenz eingestufte Produkt hat nach der Satzung und den Richtlinien des Technischen Beirats der GEV u.a. den folgenden Kriterien zu genügen:

- Das Produkt entspricht allen gesetzlichen Bestimmungen, insbesondere denen des Chemikalienrechtes und seiner Verordnungen.
- Das Produkt ist nach der Definition der TRGS 610 lösemittelfrei, sofern es sich nicht um ein Oberflächenprodukt handelt. Soweit es einer Produktgruppe nach GISCODE zuzuordnen ist, wird diese angegeben.
- Für das Produkt wird ein Sicherheitsdatenblatt nach lokalem Recht in der jeweils aktuellen Fassung erstellt.
- Krebserregende, erbgutverändernde oder fruchtschädigende Stoffe der Klassen 1A und 1B werden dem Produkt bei der Herstellung nicht zugesetzt.
- Die Prüfung des Produktes erfolgt nach der definierten „GEV-Prüfmethode“. Die VOC-Bestimmung wird dabei in einer Prüfkammer nach dem Tenax-Thermodesorptions-Verfahren mit nachgeschalteter GC/MS-Analyse durchgeführt.
- Die Einstufung in EMICODE-Klassen erfolgt entsprechend den nachstehenden Bezeichnungen und TVOC/TSVOC-Konzentrationsbereichen. Zur Produktkennzeichnung ist die zutreffende EMICODE-Klasse zu verwenden:

1) Verlegewerkstoffe, Klebstoffe und Bauprodukte

Parameter	EC 1 ^{PLUS}	EC 1	EC 2
	max. zulässige Konzentration [$\mu\text{g}/\text{m}^3$]		
TVOC nach 3 Tagen	≤ 750	≤ 1000	≤ 3000
TVOC nach 28 Tagen	≤ 60	≤ 100	≤ 300
TSVOC nach 28 Tagen	≤ 40	≤ 50	≤ 100
R-Wert basierend auf AgBB-NIK-Werten nach 28 Tagen	1	-	-
Summe der nicht bewertbaren VOC	≤ 40	-	-
Formaldehyd nach 3 Tagen	≤ 50	≤ 50	≤ 50
Acetaldehyd nach 3 Tagen	≤ 50	≤ 50	≤ 50
Summe von Form- und Acetaldehyd	$\leq 0,05$ ppm	$\leq 0,05$ ppm	$\leq 0,05$ ppm
Summe von flüchtigen K1A/K1B Stoffen nach 3 Tagen	≤ 10	≤ 10	≤ 10
Jeder flüchtige K1A/K1B Stoff nach 28 Tagen	≤ 1	≤ 1	≤ 1

2) Oberflächenbehandlungsmittel für Parkett, mineralische Böden und elastische Bodenbeläge

Parameter	EC 1 ^{PLUS}	EC 1	EC 2
	max. zulässige Konzentration [$\mu\text{g}/\text{m}^3$]		
Summe TVOC + TSVOC nach 28 Tagen	≤ 100 davon max. 40 SVOC	≤ 150 davon max. 50 SVOC	≤ 450 davon max. 100 SVOC
Formaldehyd nach 3 Tagen	≤ 50	≤ 50	≤ 50
Acetaldehyd nach 3 Tagen	≤ 50	≤ 50	≤ 50
Jeder flüchtige K1A/K1B Stoff nach 3 Tagen	≤ 10	≤ 10	≤ 10
Jeder flüchtige K1A/K1B Stoff nach 28 Tagen	≤ 1	≤ 1	≤ 1